



**Autex
Acoustics®**

Etch™

Manufacturer's Guarantee

Etch™ is manufactured by Autex Industries Ltd under ISO 9001 certified Quality Management system. This product is guaranteed to be free from manufacturing defects and carries a Manufacturer's Guarantee for a period of no less than ten years to meet all the performance properties stated within this guarantee.

Specification

Product Name	Etch™
Description	100% polyester needle punched, thermally bonded wallcovering
	Imperial
Size	51" x 164'
Thickness	1/8" - 5/32"
Printed Width	1.25m
Weight	Typically 380gsm

Physical Description/ Properties

Boiling Point:	N/A
Melting Point:	482°F
Vapor Pressure:	N/A
Specific Gravity:	Polyester 1.38
Flash point:	N/A
Explosive limits:	N/A
Solubility in water:	Not soluble
Alkalinity:	pH 7.8
Relative Vapor Density:	N/A

Service

For further information about Etch™ or any other Autex product, please contact your Autex Account Manager or visit our website.

Care and Maintenance

Maintain in accordance with the Care and Maintenance Guide available for this product.



Product Specifications

Composition

100% polyester fiber from polyethylene terephthalate (PET). Etch contains a minimum of 80% recycled polyester fiber.

Fire Ratings

Etch is a value added product made from Autex Veriface. The base material has been evaluated using the following test methods:

ISO 9705: 1993

Classification: Group 1-S
Smoke Production
Rate: <5.0m²/s
As required by NZBC C/VM2

AS ISO 9705 - 2003

Classification: Group 1
(SMOGRARC): <100m²/s²
Assessed using methodology AS ISO 9705:2003 in accordance with AS 56371:2015, as required by BCA Specification C110-4
FI 4906 dated 11th July, 2012
FAR 4055-2 dated 8th October, 2013

BS EN 13501-1:2018

Classification: B-s1,d0
Tested using BS EN ISO 11925-2:2020 and BS EN 13823:2020 and classified in accordance with BS EN 13501-1:2018, as required by BS EN 15102:2007 + A1:2011.
EUI-21-000135-C

ASTM E84 - 01

Class A, FS:20 - SD:50
01.04913.01.206a dated 29 May 2002

VOC Emissions

Autex polyester has been tested for chemical emissions in accordance with ASTM D5116 and is considered as a low VOC product. VOC concentration: 0.009 mg/m³ (7 days)

Color Fastness to Light

Etch is suitable for indoor use only. Light fastness is dependent on use and exposure. Etch has been evaluated to the following standard:
ISO 105-B02:2014
Rating: 6 (Highest = 7)

Color Fastness to Rubbing

ISO 105-X12:2016
Dry Rating: 4-5 (Highest = 5)
Wet Rating: 4-5 (Highest = 5)

Fabric Care

Blot spills from fabric quickly.
Wipe with a damp cloth.

Avoid rubbing and excessive amounts of water as this will affect the finish.

Use carpet or upholstery shampoo as directed. Blot with a clean dry cloth after each application of solution.

Finish

Non-woven. Etch has a directional grain. Product may vary from samples and batch to batch due to fiber blending and lay-up which is an inherent feature of this product.

● Autex Industries Ltd

702-718 Rosebank Rd
Private Bag 19988
Avondale 1746, Auckland
New Zealand
Freephone 0800 428 839
Phone +64 9 828 9179
Fax +64 9 828 5810

● Autex Australia Pty Ltd

166 Bamfield Road
PO Box 5099
West Heidelberg, Melbourne
VIC 3081, Australia
Freephone 1800 678 160
Phone +61 3 9457 6700
Fax +61 3 9457 1020

● Autex Acoustics Ltd

Unit J4, Lowfields Way,
Lowfields Business Park,
Elland, West Yorkshire
Hx5 9Da
United Kingdom
Phone +44 0 1422418899

● Autex Acoustics LLC

1630 Dan Kipper Dr,
Riverside, CA 92507
United States of America
Phone +1 424 203 1813

An ISO 9001, ISO 14001 and ISO 45001 certified company. The brand names and logos mentioned herein are registered or unregistered trademarks either owned or used under license by Autex Industries Limited or other members of the Autex Group. The contents of this document are protected by Copyright 2021 Autex Industries Ltd. All Rights Reserved. It is the user's responsibility to determine if the product and information presented in this document is suitable for the intended application by engaging a suitably qualified consultant. The information contained in this document is correct to the best of our knowledge at the date of its publication. To verify that this document is the most current publication please check our website or contact your Autex account manager.