TILTWALLFIXX™ TEXTURED

Polymer-Modified, Portland-Based, Textured Compound





PRODUCT DATASHEET

DESCRIPTION: TILTWALLFIXXTM TEXTURED is a polymer-modified, portland cement-based, single-component textured compound with self-curing technology (SCT). Mix TILTWALLFIXX TEXTURED with water to produce a workable, easy-to-apply mixture with excellent bonding characteristics. Liquid bonding agent is not required. It has an extended working time to allow for larger mix sizes. Once in place, it sets fast. Trowel apply TILTWALLFIXX TEXTURED to achieve a uniform finish. TILTWALLFIXX may be sponge-finished to achieve the desired appearance.

USES: Use TILTWALLFIXX TEXTURED for cosmetic patching, detailing, or finishing on tilt-up panels, precast, formed work, concrete block, and other concrete and masonry surfaces where a textured finish is desired. Durable in wet environments, it is suitable for both interior and exterior applications. TILTWALLFIXX TEXTURED may be used on vertical, overhead, and non-wearing horizontal surfaces.

APPLICATION: Apply TILTWALLFIXX TEXTURED in thicknesses from 1/16" (0.2 cm) to 1/4" (0.6 cm). It can be feathered to match existing elevations. For a smooth finish use Rapid Set WunderFixx or TILTWALLFIXX. For thicker applications, use other appropriate CTS Rapid Set® repair products. Consult your CTS Cement Representative for more information.

SURFACE PREPARATION: Application surface must be clean, sound concrete that is free from any materials that may inhibit bond, such as form release, oil, curing compound, acid, dirt and loose debris. Apply TiltWallFixx TEXTURED to a surface that is dry or saturated with no standing water. A test area should be applied to determine suitability in the repair environment.

MIXING: The use of a drill-mounted mixing paddle is recommended. Organize work so that personnel and equipment are in place before mixing. Use clean, potable water. TILTWALLFIXX TEXTURED may be mixed using 7.5 to 9.5 quarts (7.1 L to 9.0 L) per 50-lb (22.7-kg) bag. Do not exceed 9.5 quarts (9.0 L) of water per bag. Place the desired quantity of mix water into the mixing container. While the mixer is running, add TILTWALLFIXX TEXTURED. Mix to achieve a lump-free, uniform consistency. Do not retemper.

INSTALLATION: At time of installation, the surface and ambient temperatures must be between 50°F and 90°F (10°C and 32°C). TILTWALLFIXX TEXTURED has a working time of 90 minutes at a temperature of 70°F (21°C). Once in place, use a trowel to shave or cut the excess material to the desired shape. Material can be sponged for a more enhanced, textured finish. Prime and paint in accordance with the paint manufacturer's recommendations.

CURING: TILTWALLFIXX TEXTURED does not require water curing or curing compound under moderate conditions at 70°F (21°C). In dry, windy or hot conditions, mist with water to maintain a continuously wet surface until the product has achieved sufficient strength.

COLD WEATHER: Environmental and material temperatures below 70°F (21°C) may delay setting time and reduce the rate of strength gain. Lower temperatures will have a more pronounced effect. Thinner sections will be more significantly affected. To compensate

OVERVIEW

Highlights:

Polymer modified: Just add water, no bonding agent needed

Pot Life: 90+ minutes

Textured Finish: Includes fine aggregate

Excellent Bond: Bonds to concrete, block, plaster and more

Self-Curing Technology (SCT): No water curing needed under moderate conditions

Gray color

MasterFormat® 2020

03 01 30 Maintenance of Cast-In-Place Concrete

03 01 40 Maintenance of Precast Concrete

03 35 00 Concrete Finishing

Manufacturer:

CTS Cement Manufacturing Corp. 12442 Knott St. Garden Grove, CA 92841

Tel: 800-929-3030 | Fax: 714-379-8270

Web: www.CTScement.com E-mail: info@CTScement.com



for cold temperatures, keep material warm, use heated mix water, and follow ACI 306 Procedures for Cold Weather Concreting.

WARM WEATHER: Environmental and material temperatures above 70°F (21°C) may speed setting time and increase the rate of strength gain. Higher temperatures will have a more pronounced effect. To compensate for warm temperatures, keep material cool, use chilled mix water, and follow ACI 305 Procedures for Hot Weather Concreting.

YIELD & PACKAGING: TILTWALLFIXX TEXTURED is available in 50-lb (22.7-kg) bags. One 50-lb (22.7-kg) bag of TILTWALLFIXX TEXTURED will yield approximately 155 ft² (14.4 m²) at 1/16".

SHELF LIFE: TILTWALLFIXX TEXTURED has a shelf life of 12 months when stored properly in a dry location, protected from moisture, out of direct sunlight, and in an undamaged package.

USER RESPONSIBILITY: Contact your CTS technical representative for guidance when using DARK and LIGHT from the Rapid Set® Concrete Pharmacy®. Other Rapid Set Concrete Pharmacy additives are not recommended to be used with TILTWALLFIXX TEXTURED. Before using CTS products, read current technical data sheets, bulletins, product labels and safety data sheets at www.CTScement.com. It is the user's responsibility to review instructions and warnings for any CTS products prior to use.

WARNING: DO NOT BREATHE DUST. AVOID CONTACT WITH SKIN AND EYES. Use material in well-ventilated areas only. Exposure to cement dust may irritate eyes, nose, throat, and the upper respiratory system/lungs. Silica exposure by inhalation may result in the development of lung injuries and pulmonary diseases, including silicosis and lung cancer. Seek medical treatment if you experience difficulty breathing while using this product. The use of a NIOSH/MSHA-approved respirator (P-, N- or R-95) is recommended to minimize inhalation of cement dust. Eat and drink only in dust-free areas to avoid ingesting cement dust. Skin contact with dry material or wet mixtures may result in bodily injury ranging from moderate irritation and thickening/cracking of skin to severe skin damage from chemical burns. If irritation or burning occurs, seek medical treatment. Protect eyes with goggles or safety glasses with side shields. Cover skin with protective clothing. Use chemical resistant gloves and waterproof boots. In case of skin contact with cement dust, immediately wash off dust with soap and water to avoid skin damage. In case of skin contact with wet concrete, wash exposed skin areas with cold running water as soon as possible. In case of eye contact with cement dust, flush immediately and repeatedly with clean water, and consult a physician. If wet concrete splashes into eyes, rinse eyes with clean water for at least 15 minutes and go to the hospital for further treatment.

Please refer to the SDS and www.CTScement.com for additional safety information regarding this material.

LIMITED WARRANTY: CTS CEMENT MANUFACTURING CORP. (CTS) warrants its materials to be of good quality and, at its option, will replace or refund the purchase price of any material proven to be defective within one (1) year from date of purchase. The above remedies shall be the limit of CTS' responsibility. Except for the foregoing, all warranties expressed or implied, including merchantability and fitness for a particular purpose, are excluded. CTS shall not be liable for any consequential, incidental, or special damages arising directly or indirectly from the use of the materials.

△ WARNING

CANCER and REPRODUCTIVE HARM - www.P65Warnings.ca.gov

TYPICAL PHYSICAL DATA

Direct Pull Adhesion, ASTM C1583

28 days 200 psi (1.4 MPa)

