



Glazing Description

Double Pane 11/16" IGU: DG

Low-E
Low-E + Argon Gas
2x Low-E + Argon Gas
Low-E + Krypton Gas
2x Low-E + Krypton Gas

COG U-Factor

0.30
0.25
0.24
0.23
0.23

COG R-Value

3.3
4.0
4.2
4.3
4.3

Triple Pane 7/8" IGU: TG

2x Low-E + Argon Gas
2x Low-E + Krypton Gas

COG U-Factor

0.19
0.12

COG R-Value

5.6
8.3

Notes:

The COG numbers are calculated and delineated by Glazing type.

All numbers are calculated with Single Strength glass and no in-glass grids

$U = 1 / R$ & $R = 1 / U$	< U/R Factor Conversions
--	--------------------------