

TopCoat

List of proofed substances / chemical resistance

Tested floor: homogeneous sheet vinyl; curing time of sealer:
7 days Exposure time of tested substances: approx. 30 minutes

Explanation:

- Obvious damage or discolouration
- o Slight discolouration / shades
- + No discolouration or damage

	TopCoat
Inorganic acids	
Perchloric acid	+
Phosphoric acid (85 %)	—
Nitric acid (concentrated, 65 %)	—
Nitric acid (diluted, 12,5 %)	—
Hydrochloric acid (25 %)	+
Hydrochloric acid (diluted, 7,3 %)	+
Sulfuric acid (concentrated, 95 - 97 %)	—
Sulfuric acid (diluted, 9,8 %)	o
Hydrogenperoxide solution (39 %)	o / +
Hydrogenperoxide solution (3 %)	+
Inorganic bases	
Ammonia solution (concentrated, 25-30 %)	+
Ammonia solution (diluted, 10 %)	+
Barium hydroxide solution (4,73 %)	+
Sodium carbonate solution (10,6 %)	+
Sodium hydroxide solution (concentrated, 40 %)	+
Sodium hydroxide solution (diluted, 8,5 %)	+
Sodium hydrogen phosphate solution (9 %)	+
Organic acids and bases	
Formic acid	+
Acetic acid (30 %)	+
Acetic acid (diluted, 12 %)	+
Tartaric acid solution (15 %)	+

Verduren
1098 Chestnut Bend
West Plains, MO 65775
TELEPHONE NUMBER FOR EMERGENCY
Local emergency contact: 877-948-0063 | Hours: 9 a.m. to 5 p.m.

The above advice for technical application is given to the best of our knowledge and according to the latest state of technology. Therefore, if our products are used carefully heeding the advice given on their application, as well as following our suggested procedures with the materials intended for use with these products, no damage shall occur. However, our products are used outside and beyond our possible control, and are therefore subject to your own responsibility, which does not release you from the obligation to check for yourself whether our supplied products are suitable for your intended purpose and procedure. Therefore our notes and advice are not legally binding and cannot be used against us as grounds for liability - which includes the rights and protection of any third party. The relevant recommendations, guidelines and standard norms are to be observed, as well as the recognized technical rules. On publication, this product information replaces and supersedes the validity of any previous versions.